

## Product Specification

S.No.	Properties		UOM	Terra
				75
1	Substance		g/m <sup>2</sup>	75 ± 2.5%
2	Thickness		micron	103 ± 3
3	*Bulk		cc/gm	1.37 ± 0.03
4	*Breaking Length	MD	meter	4000 ± 500
		CD		2000 ± 500
5	*Tear Factor	MD	-	All
		CD		45 ± 5
6	Cobb <sub>60</sub>		g/m <sup>2</sup>	28 ± 2
7	Smoothness (Bendtsen)	I side	ml/min	200 ± 50
		II side		250 ± 50
8	*ISOBrightness (L&W Elrepho)		%	88 ± 1
9	*CIE Whiteness (L&W Elrepho)		-	155 ± 5
10	*Print Opacity (L&W Elrepho)		%	94 ± 1
11	*Wax Pick		no.	14 A Clear
12	*Stiffness	MD	° Taber	2.1 ± 0.2
		CD		1.1 ± 0.2
13	Shade		-	Reddish Blue